


# Brackish Water RO Elements

Туре	Diameter Inch	Membrane Area ft <sup>2</sup> (m <sup>2</sup> )	Salt Rejection %	Product Flow Rate gpd(m <sup>3</sup> / d)	Feed Spacer Thickness mil
TMG20-400C	8"	400(37)	99.5	10,200(38.6)	31
TMG20-440C	8"	440(41)	99.5	11,300(42.6)	28

1. Membrane Type		Cross Linked Fully Aromatic Polyamide Composite
2. Test Conditions		
	Feed Water Pressure	110 psi(0.76MPa)
	Feed Water Temperature	77°F(25°C)
	Feed Water Concentration	500 mg/l Nacl
	Recovery Rate	15%
	Feed Water pH	7
3. Minimum Salt Rejection		99.0%
4. Minimum Product Flow Rate		8,200gpd(31.0m <sup>3</sup> /d)(TMG20-400C)
		9,000gpd(34.1m <sup>3</sup> /d)(TMG20-440C)

### Dimensions



#### **Operating Limits**

Maximum Operating Pressure Maximum Feed Water Temperature Maximum Feed Water SDI15	365psi (2.5 MPa) 113°F (45°C)
Feed Water Chlorine Concentration	o Not Detactable
Feed Water pH Range, Continuous Operation	2-11
Feed Water pH Range, Chemical Cleaning Maximum Pressure Drop per Element	1-12 20psi (0.14 MPa)
Maximum Pressure Drop per Vessel	60psi (0.4 MPa)

#### **Operating Information**

- 1. For the recommended design range, please consult the latest Toray technical bulletin, design guide lines, computer design program, and/ or call an application specialist. If the operating limits given in this Product Information Bulletin are not strictly followed, the Limited Warranty will be null and void.
- 2. All elements are wet tested, treated with a 1% by weight percent sodium bisulfite storage solution, and then vacuum packed in oxygen barrier bags, or treated with tested feed water solution, and then vacuum packed in oxygen barrier bags with deoxidant inside. To prevent biological growth during short term storage, shipment, or system shutdown, it is recommended that Toray elements be immersed in a protective solution containing 500 1,000 ppm of sodium bisulfite (food grade) dissolved in permeate.
- 3. Permeate from the first hour of operation shall be discarded.
- 4. The customer is fully responsible for the effects of chemicals that are incompatible with the elements. Their use will void the element Limited Warranty.

## Notice

- 1. Toray accepts no responsibility for results obtained by the application of this information or the safety or suitability of Toray's products, either alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product combination for their own purposes.
- 2. All data may change without prior notice, due to technical modifications or production changes.

Asia and Oceania: Toray Industries, Inc. RO Membrane Products Department		Europe, Middle East and Africa: Toray Membrane Europe AG	CHINA: Toray BlueStar Membrane Co., Ltd.
Urayasu, Chiba 279-8555, Japan	13435 Danielson St, Poway, CA 92064, USA Tel: +1 858 218 2390 Fax: +1 858 486 3063	Grabenackerstrasse 8 CH-4142 Münchenstein 1, Switzerland Tel: +41 61 415 87 10 Fax: +41 61 415 87 20	No.5 Anxiang Street, Area B, Beijing Tianzhu Airport Economic Development Zone, Beijing ,101318 P.R.C. Tel: +86 10 80490552 Fax: +86 10 80485217